

HYMAX FG SERIES

Brautek HyMax FG Series hydraulic oils are formulated specially for hydraulic systems operating in the food service, beverage, and packaging industry. These premium white oil lubricants are NSF Registered and meet USDA 1998 (H1) guidelines (lubricants with incidental food contact). Brautek HyMax FG Series lubricants are manufactured in an ISO 21469 certified facility.

HyMax FG Series lubricants are fortified with oxidation inhibitors, corrosion inhibitors, as well as anti-wear additives to enhance the superior qualities offered by the Food Grade base stock. They are extended life lubricants and have the same excellent compatibility as the Brautek HyMax Series hydraulic oils.

Physical Properties

PRODUCTS	FG-15	FG-22	FG-32	FG-46	FG-68	FG-100
ISO Grade	15	22	32	46	68	100
Viscosity						
@ 40°C, cSt	15.4	22.3	32.0	42.0	68.0	97.2
@ 100°C, cSt	3.41	4.30	5.38	6.41	8.76	11.14
@ 100°F, SUS	84.1	116.7	165.4	216.0	352.0	505.0
@ 210°F, SUS	37.8	40.7	44.3	47.7	55.8	64.4
Viscosity Index	91	96	101	101	101	100
Specific Gravity	0.860	0.860	0.865	0.868	0.870	0.873
Flash Point, °F (°C)	415 (213)	405 (207)	445 (230)	445 (230)	450 (232)	445 (230)
Fire Point, °F (°C)	430 (221)	440 (227)	475 (246)	475 (246)	480 (249)	475 (246)
Pour Point, °F (°C)	-6 (-21)	0 (-18)	3 (-16)	5 (-15)	-4 (-20)	-6 (-21)
Emulsion Tendency	40/40/0 10 Mins	40/40/0 10 Mins	40/40/0 10 Mins	40/40/0 10 Mins	40/40/0 10 Mins	40/40/0 10 Mins
NSF Registered	H1	H1	H1	H1	H1	H1
ISO 21469	-	-	Yes	Yes	Yes	Yes

HyMax FG-32, FG-46 & FG-68 lubricants do not produce an iridescent appearance (sheen) on the surface of the water when tested in accordance with the U.S. Coast Guard Static Sheen Test.

Percent By Weight Phosphorous.....0.0695 Sulfur.....0.047

Shelf Life: Product shelf life is 5 years from the date of manufacture, after which the product should be recertified prior to use.

Manufactured by Klüber Lubrication NA LP • P.O. Box 131359 • Tyler, CR 2120, Texas 75713, under license from Brautek LLC

Product Data Sheet

NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor does it serve as a license to operate any patent. Due to widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suitability. Product typical properties in this publication are current.